

Ultraform[®] N 2320 U03 UNC Q600

Polyoxymethylene (POM)



Product Description

Ultraform N 2320 U03 UNC Q600 is a rapidly freezing UV stabilized general-purpose injection molding grade.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm ³	1183	1.40
Mold Shrinkage, parallel, %	294-4	2.1
Mold Shrinkage, normal, %	294-4	2.1
Moisture, %	62	
(50% RH)		0.2
(Saturation)		0.8
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (190 C/2.16 Kg), cc/10min.	1133	7.5
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		2,600
Tensile stress at yield, MPa	527	
-40C		93
23C		63
80C		33
Tensile strain at yield, %	527	
23C		9.4
Nominal strain at break, %	527	
23C		30
Flexural Modulus, MPa	178	
23C		4,000
Tensile Creep Modulus (1000h), MPa	899	1,400
Tensile Creep Modulus (1h), MPa	899	1,800
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m ²	180	
23C		6.5
Charpy Notched, kJ/m ²	179	
-30C		5
23C		5.5
Charpy Unnotched, kJ/m ²	179	
-30C		180
23C		200
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	166
HDT A, C	75	95
HDT B, C	75	156
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		1.1 X10 ⁻⁴

ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	600

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.